



## Standard Specification for Metallic-Coated, Steel-Woven Wire Fence Fabric<sup>1</sup>

This standard is issued under the fixed designation A116; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope

1.1 This specification covers metallic-coated steel fence fabric having a series of horizontal (line) wires, with vertical (stay) wires either wrapped around the line wire (hinge joint) or fixed with another separate wire to the line wire (continuous stay fixed knot joint), forming rectangular openings. The fence fabric is suitable for use in fences for farm field enclosure (to keep domestic animals in or out), for wildlife and exotic animal control, for highway or railroad right-of-way fencing (to control access), and other similar uses.

1.2 This specification covers fence fabric in various designs, tensile strength grades, and metallic coating types and grades.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- A90/A90M Test Method for Weight [Mass] of Coating on Iron and Steel Articles with Zinc or Zinc-Alloy Coatings
- A370 Test Methods and Definitions for Mechanical Testing of Steel Products
- A428/A428M Test Method for Weight [Mass] of Coating on Aluminum-Coated Iron or Steel Articles
- A510 Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A05 on Metallic-Coated Iron and Steel Products and is the direct responsibility of Subcommittee A05.12 on Wire Specifications.

Current edition approved May 1, 2011. Published May 2011. Originally approved in 1927. Last previous edition approved in 2005 as A116 - 05. DOI: 10.1520/A0116-11.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- A641/A641M Specification for Zinc-Coated (Galvanized) Carbon Steel Wire
- A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment
- A809 Specification for Aluminum-Coated (Aluminized) Carbon Steel Wire
- A856/A856M Specification for Zinc-5 % Aluminum-Mischmetal Alloy-Coated Carbon Steel Wire
- A902 Terminology Relating to Metallic Coated Steel Products

#### 2.2 U.S. Federal Standard:

Fed. Std. No. 123 Marking for Shipments (Civil Agencies)<sup>3</sup>

#### 2.3 U.S. Military Standards:

MIL-STD-129 Marking for Shipment and Storage<sup>3</sup>

MIL-STD-163 Steel Mill Products, Preparation for Shipments and Storage<sup>3</sup>

### 3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology A902.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *continuous stay fixed knot joint, n*—horizontal line wire and vertical stay wire joint made by fastening continuous stay wires to line wires by tying them together with a separate piece of knot wire at each joint.

3.2.2 *hinge joint, n*—horizontal line wire and vertical stay wire joint made by wrapping stay wire around line wires.

3.2.3 *intermediate wires, n*—line wires other than top and bottom wires.

3.2.4 *top and bottom wires, n*—line wires at the edge of the fence fabric (the top and bottom edges as erected).

### 4. Ordering Information

4.1 Orders for material under this specification shall include the following information, as necessary to describe each product ordered.

<sup>3</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

4.1.1 Name of material and joint style (woven steel fence fabric with hinge joint or continuous stay fixed knot joint);

4.1.2 Quantity (number of rolls);

4.1.3 Design Number—Number describing standard sizes and construction of the fabric as listed in [Table 1](#);

NOTE 1—The design numbers are related to the characteristics of the construction of the fence fabric. The design number indicates the number of line wires, approximate height, stay wire spacing, and size (gage) of the line and stay wires.

4.1.4 Fabric Length—When length is not specified by the order fabric is furnished to the standard length of 330 ft (101 m);

4.1.5 Tensile Strength Grade—The fabric is available in strength grades of 60, 125, and 175 (see [Table 1](#));

4.1.6 Metallic Coating Type;

4.1.6.1 Coating Type A—Made from aluminum coated wire.

4.1.6.2 Coating Type Z—Made from zinc coated wire.

4.1.6.3 Coating Type ZA—Made from Zn-5 % Al-miscmetal alloy (Zn-5Al-MM) coated wire.

4.1.7 Metallic Coating Class (see [Table 2](#));

4.1.8 ASTM designation and year of issue, and

4.1.9 Certification, or test report, or both, if required (see [Section 10](#)).

NOTE 2—A typical ordering description is as follows: Woven-steel fence fabric, hinge joint, 60 rolls, Design Number 1047-6-12 ½, roll length 330 ft, Grade 60, Coating Type Z, Coating Class 3, to ASTM A116—, with certification.

4.2 All rolls of fence fabric accepted by the purchaser shall be billed on the basis of the original length of the rolls before sampling unless changed by contractual agreement.

## 5. Material

5.1 *Wire*—The steel wire shall be coated prior to fabrication, to the coating class specified in the order, the coating weight (mass) conforming to the requirements of [Table 2](#). Coated wire shall be produced to the following applicable specifications:

5.1.1 *Coating Type A*—Specification [A809](#);

5.1.2 *Coating Type Z*—Specification [A641/A641M](#);

5.1.3 *Coating Type ZA*—Specification [A856/A856M](#).

5.2 *Coated Wire Size*—Coated wire gage sizes shown in [Table 1](#), [Table 2](#), and [Table 3](#) corresponds to steel wire gage sizes listed in Specification [A510](#), within the tolerances stated in [Section 7](#).

## 6. General Requirements

6.1 *Construction*—The sizes and constructions for fence fabric furnished under this specification shall be in accordance with the requirements of [Table 1](#) for the design number specified in the order, within the tolerances stated in [Section 7](#). Designs other than specified in the table can be manufactured upon agreement between purchaser and producer. Each design can be manufactured with hinge joint or continuous stay fixed knot joint.

6.2 *Horizontal Wire*—Horizontal wires of all woven fencing shall be furnished with tension curves, at least one tension curve per each 9 in. (229 mm) of horizontal (line) wire.

6.3 *Splices*—Splicing of the individual line wires by means of a wrap joint, mechanical fasteners, or an electric butt weld is permitted. The maximum number of line wire splices or joints shall not exceed one-half of the number of line wires in any 330 ft (101 m) (20 rod) roll of fabric. Such splices and joints shall be made in a workman-like manner and welded joints shall be coated with the corresponding Type A, Z, or ZA-coating material to provide corrosion protection equivalent to the type of coated wire being used.

6.4 *Stay Wires*—Stay wires shall be uniformly spaced and substantially perpendicular to the line wires. Tie wire used for the continuous stay fixed knot joint style fabric shall be minimum 13.5 gage and of the same coating type and class as stay wire.

6.5 *Fence Fabric Length*—The length of fence fabric in a roll shall be 330 ft (101 m) (20 rod). Fabric length other than 330 ft can be manufactured upon agreement between purchaser and producer.

6.6 *Breaking Strength*—The breaking strength of line wires shall conform to the requirements of [Table 3](#) for the grade specified in the order. There is no strength requirement for the stay wires for hinge joint style fabric. For Grade 175 continuous stay fixed knot joint style fabric, stay wire minimum tensile strength is 100 ksi (Grade 100).

## 7. Permissible Variations in Dimensions

7.1 *Wire Diameter*—The permissible variation of the wire, from the nominal diameter shown in [Table 3](#), shall be  $\pm 0.005$  in. ( $\pm 0.127$  mm). Determine the diameter using a micrometer or other suitable measuring instrument, based on the greatest and least measurement at the same cross-section, with measurement to the nearest 0.001 in. (0.025 mm). The average of the two measurements shall be considered the diameter of the test specimen.

7.1.1 *Out-of-Roundness*—Due to the mechanics of manufacture, a certain amount of out-of-roundness is expected on the stay wires of the finished fence fabric. No limits are placed on out-of-roundness of the stay wires.

7.2 *Fabric Height*—The height of the woven wire fence fabric (center-to-center distance between top and bottom wires) shall not vary more than 1 in. (25 mm) from the specified height shown in [Table 1](#). The specified height of the fence fabric is based on the sum of the line wire spacings shown in [Fig. 1](#), [Fig. 2](#), or [Fig. 3](#).

7.3 *Stay Wire Spacing*—The spacing between individual pairs of stay wires, shall not vary from the nominal dimensions more than ⅜ in. (10 mm) for 3 in. and 6 in. spacing and no more than ¼ in. (19 mm) for 12 in. spacing product.

7.4 *Horizontal (Line) Wire Spacing*—The spacing between horizontal wires shall be as illustrated in [Fig. 1](#), [Fig. 2](#), and [Fig. 3](#). Alternative spacing to that illustrated in [Fig. 1](#), [Fig. 2](#), and [Fig. 3](#) is acceptable for given design number when agreed upon between purchaser and producer, providing that the total number of line wires remains unchanged. The spacing between individual pairs of horizontal wires shall not vary from the accepted nominal dimensions by more than ⅜ in. (10 mm).

**8.6 Inspection for General Workmanship**—For the purpose of inspection, a maximum of two rolls from the lot, as described in **8.2**, shall be subjected to observations for the line and stay wire spacing, overall length, and workmanship.

8.6.1 Instead of inspecting for length by unrolling full rolls, the purchaser and manufacturer have the option of agreeing on a weight per roll related to the fabric design, or measuring tools employed during manufacturing. The purchaser still reserves the right to confirm the length by actual measurement.

## 9. Retests and Rejection

9.1 If one or more of the test specimens from a sample roll of fence fabric fail the weight-of-coating test, or the breaking strength test, the lot shall be subjected to retests. For retest purposes, four additional rolls for each 50 rolls offered shall be sampled. The lot size then becomes 50. Test specimens shall be cut in accordance with **8.3** or **8.4** as appropriate.

9.2 If more than four of the 24 retest specimens for weight-of-coating fail to meet the requirements of **Table 2**, or if any of the retest specimens has less than 75 % of the specified coating weight, the entire lot represented by the retest specimens may be rejected.

9.3 If more than 3 of 16 retest specimens for breaking strength fail to meet the requirements of **Table 3**, or if any of the retest specimens has less than 90 % of the specified breaking strength, the entire lot represented by the retest specimens may be rejected.

9.4 If instead of rejecting the entire lot as provided for in **9.2** or **9.3**, the producer may test specimens from every roll as provided for in **8.3** or **8.4** and resubmit those rolls meeting specification requirements.

9.5 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to

the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

## 10. Certification

10.1 When specified in the purchase order or contract, a producer's or supplier's certification shall be furnished to the purchaser that the material was manufactured, sampled, tested, and inspected in accordance with this specification and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

## 11. Packaging and Package Marking

11.1 Unless otherwise specified, packaging, marking, and loading for shipment shall be in accordance with Practices **A700**.

11.2 When specified in the contract or order, and for direct procurement by or direct shipment to the U.S. Government, when Level A is specified, preservation, packaging, and packing shall be in accordance with the Level A requirement of MIL-STD-163.

11.3 When specified in the contract or order, and for the direct procurement by or direct shipment to the U.S. Government, marking for shipment, in addition to requirements specified in the contract or order, shall be in accordance with MIL-STD-129 for U.S. military agencies and in accordance with Fed. Std. No. 123 for U.S. Government civil agencies.

## 12. Keywords

12.1 fence fabric; fencing material; metallic coated steel wire; steel wire; wire

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*